

DESOPON[®] SO

Major component

- Sulfonic, phosphorylated natural oil and synthetic oil

- Good penetration and fixation. Resistance to migration. Give crust resistance to ironing and wash-fastness.
- Give leather soft, moistened, and waxy feel.
- Stable to acid and electrolyte. When added during pickling, improve softness of leather.

Specification

Appearance(25°C):	Soft paste
Color:	Yellowish brown
pH(10% aqueous solution, 25°C):	7.0±1.0
Active matter %:	52.0±2.0
Short chain chlorinated paraffin:	Comply with EU REACH laws and regulations
APEO:	Comply with EU REACH laws and regulations

Application

- Recommended main fatliquoring formulation for cowhide nappa shoe upper (in terms of shaved wet-blue):

DESOPON SO	5.0%
DESOPON QL	2.0%
DESOPON DPF	4.0%
- Recommended main fatliquoring formulation for cowhide upholstery (in terms of shaved wet-blue):

DESOPON SO	6.0%
DESOPON DPF	4.0%
DESOPON SK70	4.0%
DESOPON QL	2.0%

DESOPON[®] SO

- Recommended main fatliquoring formulation for sheepskin garment (in terms of shaved wet-blue):

DESOPON SO	5.0%
DESOPON DPF	4.0%
DESOPON SK70	3.0%
DESOPON QL	3.0%

Safety

- This is not a hazardous chemical.
- Observe all the precautions required for handling chemicals.
- Read attentively and observe all the recommendations in our **Material Safety Data Sheet**.

Transportation and Storage

- The product has a shelf life of at least one year if it is stored in its tightly sealed original packaging at temperatures between 5°C and 35°C.
- This product should be stored in a cool and dry place, lidded and keep upright. Avoid direct exposure to the sun or frost.
- Appearance may change during storage, the freezing point is about 30-40°C, if lamination occur, stir well before use, properties will not be affected.
- Re-seal the package immediately after using, use up as soon as possible once the package is opened.
- Read attentively and observe all the recommendations in our **Material Safety Data Sheet**.