

DESOPON[®] SK70

Major component

- Synthetic oil

Property

- Combine well with fiber. Give light-weight leather resistance to dryness, heat, vacuum and washing.
- Excellent lightfastness. Suitable for manufacturing light-colored leather.

Specification

Appearance(25°C):	Paste
Color:	White to yellowish
Active matter %:	43.0±2.0
pH(10% aqueous solution, 25°C):	6.0±1.0
Ionicity:	Anionic
APEO & Short chain chlorinated paraffin:	Comply with EU REACH laws and regulations

Application

Recommended formulation (in terms of shaved wet-blue)

- Main fatliquoring for cowhide nappa shoe upper:

DESOPON SK70	4.0%
DESOPON SO	3.0%
DESOPON QL	2.0%
DESOPON DPF	3.0%

- Main fatliquoring for cowhide upholstery:

DESOPON SK70	6.0%
DESOPON DPF	4.0%
DESOPON QL	3.0%
DESOPON SO	3.0%

DESOPON[®] SK70

- Main fatliquoring for sheepskin garment:

DESOPON SK70	5.0%
DESOPON SO	3.0%
DESOPON QL	3.0%
DESOPON DPF	4.0%

Safety

- This is not a hazardous chemical.
- Observe all the precautions required for handling chemicals.
- Read attentively and observe all the recommendations in our **Material Safety Data Sheet**.

Transportation and Storage

- The product has a shelf life of at least one year if it is stored in its tightly sealed original packaging at temperatures between 5°C and 35°C.
- This product should be stored in a cool and dry place, lidded and keep upright. Avoid direct exposure to the sun or frost.
- Appearance may change during storage, if lamination occur, stir well before use, properties will not be affected.
- Re-seal the package immediately after using, use up as soon as possible once the package is opened.
- Read attentively and observe all the recommendations in our **Material Safety Data Sheet**.