

DESOPON[®] LQ-5

Major component

- Alkane, surfactant

Property

- Stable to electrolyte, suitable for pickling, tanning, retanning and other process of leather or fur.
- Excellent lightfastness, especially for fatliquoring of chrome free tanned or chrome tanned white leather.
- Excellent emulsifying capacity. Good compatibility. Improve stability of other fatliquors.

Specification

Appearance(25°C):	Emulsion
Color:	White
Active matter%:	55.0±2.0
pH(10% aqueous solution, 25°C):	6.5±1.0
Ionicity:	Anionic
APEO:	Comply with EU REACH laws and regulations

Application

- Recommended process for tanning:
Pickling liquid 50 % Room temperature
DESOPON LQ-5 0.5~2.0% Run 30 min before adding chrome powder.
- Recommended process for main fatliquoring:
DESOPON LQ-5 2.0~4.0% Mix with other oil before adding.

DESOPON[®] LQ-5

Safety

- This is not a hazardous chemical.
- Observe all the precautions required for handling chemicals.
- Read attentively and observe all the recommendations in our **Material Safety Data Sheet**.

Transportation and Storage

- The product has a shelf life of at least one year if it is stored in its tightly sealed original packaging at temperatures between 5°C and 35°C.
- This product should be stored in a cool and dry place, lidded and keep upright. Avoid direct exposure to the sun or frost.
- Appearance may change during storage, if lamination occur, stir well before use, properties will not be affected.
- Re-seal the package immediately after using, use up as soon as possible once the package is opened.
- Read attentively and observe all the recommendations in our **Material Safety Data Sheet**.