

# DESOADDI® AS5332

## Major component

- Mixture of polymer adhesives, fillers and auxiliaries.

## Property

- Directly used for roller, and give a good covering ability.
- Excellent fall resistance, bending resistance.
- Excellent resistance to cut through on embossing.
- Excellent moisturizing performance, adapt to continuous roll coating without drying.
- Suitable for all kinds of heavy damaged hides.

## Specification

Appearance(25°C):	White pastes
Solid content (%):	~30.0
pH(10.0% aqueous solution, 25°C):	~8.5
Ionicity:	Anionic

## Application

- Apply it on the damaged hides by roller.
- 5% pigment can be added when it was applied on dyed leathers.
- The leather should be hung up for about 4 hours after being dealt with this product. And polishing it with 400# sandpaper will be better.

## Safety

- This is not a hazardous chemical.
- Observe all the precautions required for handling chemicals.
- Read attentively and observe all the recommendations in our **Material Safety Data Sheet**.

# DESOADDI<sup>®</sup> AS5332

## Transportation and Storage

- The product has a shelf life of at least one year if it is stored in its tightly sealed original packaging at temperatures between 5°C and 35°C.
- The product should be stored in a cool and dry place, with no throwing, avoid direct exposure to the sun or rain or humidity.
- This product may be stratified during storage, and the application effect will not be affected if using it after mixing evenly.
- Re-seal the package immediately after using, use up as soon as possible once the package is opened.
- Read attentively and observe all the recommendations in our **Material Safety Data Sheet**.