

Formaldehyde free amino resin

Decision Product Catalogue

DESOATEN NFR

Major component

•condensate of amino compound

Property

• Give leather fullness and softness

•Has excellent penetration and selective filling to lessen the leather part differences

- •Has good light resistance and heat resistance
- •The retaned leather has a fine grain and very good milling, buffing effect
- •Formaldehyde free

			C •				
\sim	n	\mathbf{c}	11	<u> </u>	11	\cap	n
\mathbf{D}	U	U	fi	L.	ЧI	U	

Appearance(25°C):	Powder		
Color:	Yellow		
Solid content %:	≥92.0		
pH(10% aqueous solution, 25°C)	6.5±1.0		
charge	anion		

Application

Recommended dosage (in terms of shaved wet blue)
Cowhide shoe upper: DESOATEN NFR 4.0% ~ 10.0%
Cowhide upholstery: DESOATEN NFR 3.0~6.0%
Garment: DESOATEN NFR 2.0~5.0%

Safety

- This is not a hazardous chemical.
- •Observe all the precautions required for handling chemicals
- •Read attentively and observe all the recommendations in our Material Safety

This information is based on our current level of knowledge and experience. We do not make any promise or guarantee. Before use, the customer is still necessary to test the product in order to determine whether it is suitable for the objective production conditions and demand.



Formaldehyde free amino resin

Decision Product Catalogue

Data Sheet

Transportation and Storage

•Shelf life is two year (0-40°C) if following conditions are fulfilled.

•This product should be stored in a shady and cool place, lidded and keep upright. Avoid direct exposure to the sun or frost.

•This product tends to form lumps. If it is not expired, properties will be not affected

•Re-seal the package immediately after using, use up as soon as possible once the package is opened.

•Read attentively and observe all the recommendations in our **Material Safety Data Sheet.**

This information is based on our current level of knowledge and experience. We do not make any promise or guarantee. Before use, the customer is still necessary to test the product in order to determine whether it is suitable for the objective production conditions and demand.