

Tannin Derived From Phenol

Decision Chemical Product Catalogue

DESOATEN® SAT-P

Major component

•Phenol derived condensate

Property

- •Excellent filling property, give full leather with tight grain.
- •Excellent light and heat resistance, suitable for white leather.
- •It has astringency similar to tannin extract, after falling soft, the patten is very even.
- •Low content of formaldehyde, suitbale for infant leather.

Specification

Appearance(25°C): Color: Solid content%: pH(10% aqueous solution, 25°C): Charge: Powder Light brown ≥95 5.0 approx. Anionic

Application

Recommended dosage(in terms of shaved wet blue):

- •For cowhide shoe upper: **DESOATEN SAT-P** 4.0%~10.0%
- •For cowhide furniture leather: DESOATEN SAT-P 2.0%~8.0%
- •For garment leather: **DESOATEN SAT-P** 1.0%~5.0%

Safety

•This is not a hazardous chemical.

- •Observe all the precautions required for handling chemicals.
- •Read attentively and observe all the recommendations in our Material Safety

This information is based on our current level of knowledge and experience. We do not make any promise or guarantee. Before use, the customer is still necessary to test the product in order to determine whether it is suitable for the objective production conditions and demand.



Tannin Derived From Phenol

Decision Chemical Product Catalogue **Data Sheet.**

Transportation and Storage

•The product has a shelf life of at least one year if it is stored in its tightly sealed original packaging at temperatures between 0°C and 40°C.

• This product should be stored in a cool and dry place, lidded and keep upright. Avoid direct exposure to the sun or frost.

•Color may turn darker during storage, which does not affect property.

• Re-seal the package immediately after using, use up as soon as possible once the package is opened.

• Read attentively and observe all the recommendations in our Material Safety Data Sheet.

This information is based on our current level of knowledge and experience. We do not make any promise or guarantee. Before use, the customer is still necessary to test the product in order to determine whether it is suitable for the objective production conditions and demand.