DESOBATE® ESP

Major component

• Protease preparation.

Property

• It can effectively decompose non-fibrous proteins within the hide, such as albumin, globulin, and interfibrillar mucopolysaccharides, thereby cleansing impurities and dirt from the leather.

• It can effectively reduce soaking time, facilitate the penetration and uniform action of chemical materials,and enhance the softness, breathability,and lightness of the leather.

• It can reduce growth marks on the hide and fundamentally alter the grain structure.This prevents wrinkles from reappearing in subsequent processes and improves the leather yield.

• It acts gently,avoiding excessive fiber loss,and is compatible with soaking aids.

Specification

Appearance(25°C):	Powder
Color:	Pale yellow to light brown
pH(10% aqueous solution, 25°C):	9.0±1.5

Application

• The dosage depends on the type,condition,and usage conditions of the raw hides.

• Applied in the soaking process for various types of raw hides:

DESOBATE ESP recommended dosage: 0.1-0.5%

The information contained in this manual is not a unilateral commitment by our company or a contractual provision. Users are responsible for confirming product suitability under actual conditions.

DESOBATE® ESP

Safety

- This is not a hazardous chemical.
- Observe all the precautions required for handling chemicals.
- Read attentively and observe all the recommendations in our **Safety Data Sheet.**

Transportation and Storage

- The product has a shelf life of one year if it is stored in its tightly sealed original packaging at temperatures below 25°C.
- The product should be stored in a cool and dry place，with no throwing，avoid direct exposure to the sun or rain or humidity.
- Re-seal the package immediately after using, use up as soon as possible once the package is opened.
- Read attentively and observe all the recommendations in our **Safety Data Sheet.**

The information contained in this manual is not a unilateral commitment by our company or a contractual provision. Users are responsible for confirming product suitability under actual conditions.