DESOPON® WP1

Major component

• Aqueous dispersion of silicone-containing polymers

Property

• Suitable for the waterproof treatment of various chrome-tanned leathers. Excellent waterproof performance after being fixed by metal salts.
• Good permeability, evenly distributed in the skin to achieve excellent overall hydrophobicity.
• The leather after treatment feels fullness, soft, and has excellent light resistance and high temperature yellowing resistance.

Specification

Appearance (25 °C):	Soft paste
Color:	White to beige
Active Matter Content, %:	45.0±2.0
pH (10.0% aqueous solution, 25 °C):	8.5±1.0
Ionicity:	Anionic

Application

• Pickling, chrome tanning (in terms of limed pelt):	**DESOPON WP1**	1.0~2.0%
• Wetting, chrome retanning (in terms of shaved weight):	**DESOPON WP1**	1.0～3.0%
• Fatliquoring (in terms of shaved weight):	**DESOPON WP1**	1.0~3.0%

Safety

• This is not a hazardous chemical.
• Observe all the precautions required for handling chemicals.
• Read attentively and observe all the recommendations in our **Safety Data Sheet.**

The information contained in this manual is not a unilateral commitment by our company or a contractual provision. Users are responsible for confirming product suitability under actual conditions.

DESOPON® WP1

Transportation and Storage

- The product has a shelf life of one year if it is stored in its tightly sealed original packaging at temperatures between 5°C and 35°C.
- This product should be stored in a shady and cool place, lidded and keep upright. Avoid direct exposure to the sun or frost.
- Appearance may change during storage, if lamination occur, stir well before use, properties will not be affected.
- Re-seal the package immediately after using, use up as soon as possible once the package is opened.
- Read attentively and observe all the recommendations in our **Safety Data Sheet.**

The information contained in this manual is not a unilateral commitment by our company or a contractual provision. Users are responsible for confirming product suitability under actual conditions.